



# TECHNICAL DATA SHEET

## Wicklow Range

**Mineral oil based anti-wear hydraulic oils Product code: Refer to table**

**Description:** The Wicklow range of hydraulic fluids is manufactured from highly refined base stocks which possess good oxidation resistance and thermal stability. They are fortified with carefully selected additives to further improve performance characteristics including anti-corrosion to protect the system should water be present, anti-wear to reduce wear in pumps used in hydraulic systems, anti-oxidants and antifoam.

**Benefits:**

- Incorporates inhibitors for protection against all forms of corrosion
- Good anti-foaming and air release properties
- Good demulsification characteristics
- Excellent anti-wear performance
- High oxidation resistance and thermal stability
- Suitable for the majority of hose materials

**Applications:** The Wicklow range of hydraulic oils is suitable for a wide variety of applications. These include industrial hydraulic systems, agricultural and plant equipment, mobile units such as jacks, lightly loaded gears and many others.

**Product Specification:**

DIN	51524 Part 2 category HLP
ISO	6743/4 category HM
Denison	HF-2 TP-02100 Filterability Test
Sperry Vickers	M-2950-S I-286-S
Afnor	NF E 48-600
Thyssen	TH N-256132
US Steel	127 SEB 181.222
VDMA	24318

**Typical Test Data:**

Wicklow	3	5	10	15	22	32	37
Specific Gravity @ 15.6°C	0.822	0.827	0.850	0.860	0.865	0.873	0.875
Kinematic Viscosity @ 40°C (cSt)	3.0	5.0	10.0	15.0	22.0	32.0	37.0
Kinematic Viscosity @ 100°C (cSt)	-	-	2.62	3.38	4.29	5.36	5.87
Viscosity Index	-	-	91	95	100	100	100
Flash Point (COC °C)	-	-	162	183	195	215	217
Pour Point (°C)	-	-	-	-	-33	-33	-33



# TECHNICAL DATA SHEET

<b>Wicklow</b>	<b>46</b>	<b>68</b>	<b>100</b>	<b>150</b>	<b>220</b>	<b>320</b>	<b>460</b>
Specific Gravity @ 15.6°C	0.878	0.880	0.889	0.890	0.893	0.895	0.901
Kinematic Viscosity @ 40°C (cSt)	46.0	68.0	100.0	150.0	220.0	320.0	460.0
Kinematic Viscosity @ 100°C (cSt)	6.75	8.75	11.4	15.0	19.4	24.7	31.3
Viscosity Index	100	100	100	100	100	99	98
Flash Point (COC °C)	220	224	228	231	233	235	245
Pour Point (°C)	-32	-31	-27	-	-	-	-

Health and Safety: Please refer to the safety data sheet, a copy of which is freely available to all our customers.